

HS 5 : 1 PRIMER FILLER

DEFINITION

VERSIS are high solid, low emission, 2k acrylic primers that guarantee complete all-purpose use thanks to the 3 application methods available:

- High build filler
- Primer Surfacer
- Non sanding primer

In tandem its colour range ensures the equality of the finish whichever colour and filling power is used:

- S1.- white
- S4.- grey
- S7.- black

Moreover, the primers of the VERSIS line fulfil the EU environmental legislation regarding VOC emissions.

PHYSICAL CHARACTERISTICS

Nature: Acrylic 2K
Colour: White, grey, black
Specific weight: 1,4 kg/l at 20°C

	<i>High build filler</i>	<i>Primer Surfacer</i>	<i>Non sanding</i>
Dry film thickness:	80 microns	50 microns	15 microns
VOC:	407 g/l	487 g/l	497 g/l
Yield:	6 - 7 m ² /l	8 -10 m ² /l	16 - 18 m ² /l

Per coat
Mixing application
Per coat

AUXILIARY PRODUCTS

KX44 Slow hardener NS21 Non sanding convertor
KX45 Standard hardener VOC PLUS Low Voc Additive Standard
KX46 Fast hardener VOC PLUS Low Voc Additive Slow

		
<i>T° (°C)</i>	<i>Hardener</i>	
< 18	KX46	KX46
18 - 25	KX45	KX45 - KX46
> 25	KX44	KX44 - KX45

SURFACE PREPARATION

Surfaces: Sanded and degreased OEM paints, cataphoresis (*), polyester putties, steel, galvanized steel, aluminium or polyester according to method of application.

	High build filler	Primer Surfacer	Non sanding
	P240	P240 - P320	P400
	√	√	√

(*) On cataphoresis it can be applied on non sanded degreased surface

MIXING RATIO

		High build filler		Primer Surfacer		Non sanding	
		Vol	Weight	Vol	Weight	Vol	Weight
	Versis	5	100	5	100	2	100
	Hardener	1	15	1	15	1	35
	NS21	-	-	-	-	1	35
	VOC PLUS Low Voc Additive Standard	-	-	1	13	-	-
	F/4 at 20°C	55"		25"		16"	
 KX45	20°C	20' - 30' (*)		40'		20'	
	25°C	15' - 25' (*)		30'		15'	
	30°C	10' - 20' (*)		25'		10'	

(*) Pot life data adding 5% of thinner

APPLICATION METHOD

		High build filler	Primer Surfacer	Non sanding
	HVLP	1,7 - 1,9	1,5 - 1,7	1,2 - 1,4
		2,5 - 3	2 - 2,5	2 - 2,5
	Coats	2 - 3	2	1 - 2
	20°C	5'	5' - 10'	3'

DRYING TIMES


		High build filler	Primer Surfacer	Non sanding
 20°C	KX44 - KX45	-	-	Min 15' Max 60'
 20°C	KX44	4 h	3 h	-
	KX45	3 - 4 h	2 - 3 h	> 1 h *
	KX46	3 h	2 h	-
 60°C	KX44 - KX45	25'	20'	-
 Medium wave 60cm	FLASH OFF	5'	5'	-
	FULL BAKE	20'	15'	-
 Short wave 80cm	FLASH OFF	5'	5'	-
	FULL BAKE	10'	10'	-

(*) In case of superficial imperfections, it can be sanded after 15' at 20°C

SANDING

		High build filler	Primer Surfacer	Non sanding
 ORBITE 3 - 5	INITIAL	P320	P400	-
	FINAL	P500	P500	SANDING PAD MICROFINE
	INITIAL	P600	P600	-
	FINAL	P800	P800	P1000

COLOUR TABLE

	Colours	Mixing ratio S1 : S7	Recommended finishes
S1		100 : 0	White
S2		90 : 10	Orange Yellow Blue Metallic light green
S3		70 : 30	Metallic light grey Medium yellow
S4		50 : 50	Metallic medium grey Dark yellow Blue Medium green
S5		30 : 70	Metallic medium red Metallic dark grey
S6		5 : 95	Metallic dark blue Metallic dark green
S7		0 : 100	Black Metallic dark red

EQUIPMENT CLEANING

Clean with a cleaning thinner before the pot life has expired.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

GUARANTEE

One year in unopened original packaging.

SUGGESTION:

Dilute with 5% of the high filling power primer when applied to temperatures up to 25°C, so we will obtain a better application and levelling.

For any technical information contact with our Customer Attention Service or our Technical Department. ROBERLO SA declines any responsibility due to an incorrect use of the product.