



# AIRCOLOR PLASTIC PRIMER

## H38

VERSION: 180528  
Page:1/2

### ADHESION PRIMER


#### DEFINITION

**AIRCOLOR PLASTIC PRIMER** is applied directly as a primer and has excellent adhesion on all plastic exterior and interior parts, including bumpers, mirrors and other plastic parts. Topcoat can be applied after approximately 10 minutes air dry at 20°C

#### PHYSICAL CHARACTERISTICS





<b>Propellant:</b>	BP
<b>Colour:</b>	Colourless
<b>Specific weight:</b>	0,8 kg/l a 20°C
<b>Yield:</b>	2 m <sup>2</sup> /spray
<b>Dry film thickness:</b>	4 µ/coat
<b>Resistance of the container to heat:</b>	< 50 °C
<b>VOC:</b>	738 g/l Application 2004/42/EC - IIB (e)(840)

#### SURFACE PREPARATION

PROCESS	Plastics (*)
 ROBRITE VF DA93	✓

(\*) PP, PP/EPDM, ABS, SAN, PC, PA, PUR-RIM, R-TPU, PPO, PBT, PUR flexible foam, UP-GF plastics


#### APPLICATION

			
2'	20-25 cm	1 coat	10'

#### REMARKS

Shake the aerosol before use for 2 minutes after hearing the steel mixing balls move. Carry out test spray.

### EQUIPMENT CLEANING



*After use, turn  
can upside  
down and spray  
for several  
seconds*

### SAFETY

Follow instructions on the product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

### STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

### SHELF LIFE

One year in unopened original packaging.

For any technical information contact with our Customer Attention Service or our Technical. Department. ROBERLO SA declines any responsibility due to an incorrect use of the product.