



UNIX 550HS-NEW FORMULA

E95

VERSION: 230919
Page: 1/3

FAST REPAIR CLEAR COAT

DEFINITION

2K Clearcoat high solids content, easy to apply, specially designed for use in partial repairs (2-3 pieces), with drying and application times that allow optimization and reduction in oven time, maintaining high levels of finish.


PHYSICAL CHARACTERISTICS

Nature:	Acrylic 2K	
Colour:	Colourless	
Specific weight:	0,990 kg/l at 20°C	
Viscosity CF/4:	18"-19" at 20°C	
Dry film thickness:	35-45 microns	
Yield:	9-10 m ² /l	
Solids content:	57 %	Unix 550HS
	53 %	Application (100:50 vol)
	51 %	Application (100:50:5 vol)
	49 %	Application (100:50:10 vol)
	VOC:	425 g/l
	460 g/l	Application (100:50 vol)
	478 g/l	Application (100:50:5 vol)
	500 g/l	Application (100:50:10 vol)

AUXILIARY PRODUCTS

P5000 Standard Hardener
C355 Standard Hardener

S322 Standard thinner



<i>T^a</i> (°C)	<i>Hardener</i>	<i>Hardener</i>	<i>Thinner Optional</i>
18 - 25	P5000/C355	P5000/C355	S322

SURFACE PREPARATION

Apply **Unix 550 HS-NF** on the basecoat after the flash off time recommended by the manufacturer.
Catalysing the base coat will enhance the final finish.

MIXING RATIO

Unix 550HS-NF					
			20°C		
C355	100:50:5-10 Volume		18"	1 h	
P5000	100:49:5-9 Weight	2 : 1	F/4		

APPLICATION METHOD

	mm	bar	cm		
	1,2-1,4	2-2,5	15 - 20	2	5'
	1,3-1,5	4	15 - 20		
	1,2-1,3	2	10		

DRYING TIMES

20° C						50° C			Short wave IR		
										FLASH OFF	FULL BAKE
P5000/ C355	15'	45'	1h15'	2h	2h 30'	P5000/ C355	10'	1h	Not recommended		

REMARKS

Humidity and temperature affects clear coat components so the application equipment should be absolutely dry, keep the clear coat and hardener at temperatures not below 15°C and not higher than 30°C.

Close the hardener container immediately after use.

When relative humidity is higher than 70% and/or temperatures lower than +10°C it is recommended to dry at 50°C.

We recommend not to over-apply on flat applications.

EQUIPMENT CLEANING

Use a cleaning thinner before the pot life has expired.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

GUARANTEE

One year in unopened original packaging.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO S.A.U reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

*All clauses contained herein apply to any future changes or modifications.
For any additional technical information please consult with our Customer Service or our Technical Department.*